

I PRICE GROUP

BOND

BOND

polyester 100%, weight 250 g/m2 +/-5%, abrasion 100 000 Martindale cycles (EN ISO 12947-2), resistance to pilling 5 (EN ISO 12945-2), light fastness 6 (EN ISO 105-B02), non-flammability certificate (BS EN 1021-1) (BS EN 1021-2), CRIB 5, BS 7176 Medium Hazard, 11M(UNI 9175)



II PRICE GROUP

PASTEL, ROCCIA, CHARLES, CHARLES STUDIO DESIGN

PASTEL

polyester 100%- TREVIRA CS,weight 260g/m2 +/-5%, abrasion 80 000 Martindale cycles, resistance to 5 (EN ISO 12945), light fastness 6 (EN ISO 105-B02), non-flammability certificate (EN 1021-1, EN 1021-2: Crib 5, BS 7176 Medium Hazard; C1, M1, B1, IMO A 652(16), IMO A 471(XII)



ROCCIA

100% polyester-TREVIRA CS weight 250g/m2 +/-5%, abrasion 70 000 Martindale cycles (UNI EN ISO 12947/2), resistance to pilling 5 (EN ISO 12945/2), light fastness 6 (EN ISO 105-B02),fastness to rubbing wet:4 (UNI EN ISO 105-X12) dry:5 (UNI EN ISO 105-X12), non-flammability certificate: EN 1021-1:2006 EN 1021-2:2006 BS 7176:2007 (Medium Hazard); BS 6852:2006 (Crib 5); NFP 92-501-1 (M1), DIN 4102-1 (B1), IMO Res. A 652 (16) Part 8 UNI 9174-UNI 8456 (C1), AM 18(NF D 60013) UNI 9175 Class 1 IM



CHARLES

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Vlet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently.



CHARLES STUDIO DESIGN AVAILABLE AT SELECTED DISTRIBUTORS

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Vlet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently. *Extended delivery time



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

III PRICE GROUP

CRISP, FAME, SYNERGY

CRISP

93% wool, 7% polyamide weight: 328 g/m2 abrasion: 200000 Martindale cycles (EN ISO 12947-2) resistance to piling 4-5 (EN ISO 12945-2) light fastness 5-7 (EN ISO 105-B02) rubbing fastness 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1,2; BS 5852 0&1; Calif. Bull.117-E class 1; IMO MS c307(88)Annex 1 part 8; MED certificate IMO

FAME

95% wool, 5% polyamide weight: 450 g/m2 abrasion: 200 000 Martindale cycles (EN ISO 12947-2) resistance to piling: 4 (EN ISO 12945-2) light fastness: 5-7 (EN ISO 105-B02) rubbing fastness: 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1&2; BS 5852:2006 (Crib 5); BS 5852 0&1; UNI 9175 class 1 IM; Calif.Bull.117-E class 1 cleaning: dry cleaning

SYNERGY

Composition:virgin wool 95%, polyamide 5%; Weight: 400g/m2 ±5% Abrasion Resistance > 100 000 Martindale cycles. Fastness to Rubbing: 4 (ISO 105-X12) Light Fastness: 5 (ISO 105-B02) Flammability: EN 1021-1&2 Cigarette & Match NF D 60-013 UNI 9175 Classe 1 IM BS 7176 Low Hazard



IV PRICE GROUP

REMIX

REMIX

Composition: 90% wool, 10% nylon Weight: ok 300 g/m2 Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021 - 1/2 BS 5852 Part 1 Onorm B1/Q1 UNI 9175 IMO A.652(16) Crib 5 and B2 Producer: kvadrat Denmark



METAL

METAL

METAL

colors frames

V PRICE GROUP - STUDIO DESIGN

STEELCUT TRIO 2 , TURNBERRY , TROON , ACCESSOIRE

STEELCUT TRIO 2 STUDIO DESIGN

Composition: 90% wool, 10% nylon; Abrasion Resistance: 100 000 Martindale cycles; Fastness to Rubbing 3-4 (EN ISO 12945); Light Fastness: 5-7 (ISO 105-B02); Flammability: EN 1021-1/2; BS 5852 part 1; DIN 4102 B2; Önorm B1/Q1; NF D 60 013; UNI 9175 1IM; US Cal. Bull. 117, – 2013; IMO FTP Code 2010: Part 8



TURNBERRY STUDIO DESIGN

Composition: 100% wool; Weight: 586 g/m2 ± 5%; Abrasion Resistance: 43 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5



TROON STUDIO DESIGN

Composition 92% wool, 7% nylon; Weight: 37 g/m2 ± 5%; Abrasion Resistance: 60 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5



ACCESSOIRE STUDIO DESIGN

Composition: 85% wool 15% polyamide; Weight: 350 g/m2 +/- 5%; Abrasion Resistance 50 000 Martindale cycles; Fastness to Rubbing: 4 (EN ISO 105-C06); Light Fastness: 5-7 (EN ISO 105-B02); Flammability: BS EN 1021-1 BS EN 1021 - 2



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.