

I PRICE GROUP

BOND

BOND

polyester 100%, weight 250 g/m2 +/-5%, abrasion 100 000 Martindale cycles (EN ISO 12947-2), resistance to pilling 5 (EN ISO 12945-2), light fastness 6 (EN ISO 105-B02), non-flammability certificate (BS EN 1021-1) (BS EN 1021-2), CRIB 5, BS 7176 Medium Hazard, 11M(UNI 9175)



II PRICE GROUP

FIGHTER, PASTEL, ROCCIA, CHARLES, CHARLES STUDIO DESIGN

FIGHTER

polyester 100%.weight 365 g/m2, abrasion 130 000 cycles Martindale , resistance to pilling 4-5 (EN ISO 12945-2), light fastness >5 (EN ISO 105-B02), non-flammblity certificate (BS EN 1021-1, BS EN 1021-2, BS 5852(part 10,1), Q1 UK, UNI 9175 Class 1 IEMME)



PASTEL

polyester 100%- TREVIRA CS,weight 260g/m2 +/-5%, abrasion 80 000 Martindale cycles, resistance to 5 (EN ISO 12945), light fastness 6 (EN ISO 105-B02), non-flammblity certificate (EN 1021-1, EN 1021-2, Crib 5; BS 7176:2007 (Medium Hazard); BS 5852:2006 (Crib 5); NFP 92-501-1 (M1), IMO A 471(XII))



ROCCIA

100% polyester-TREVIRA CS weight 250g/m2 +/-5%, abrasion 70 000 Martindale cycles (UNI EN ISO 12947/2), resistance to pilling 5 (EN ISO 12945/2), light fastness 6 (EN ISO 105-B02),fastness to rubbing wet:4 (UNI EN ISO 105-X12) dry:5 (UNI EN ISO 105-X12), non-flammblity certificate: EN 1021-1:2006 EN 1021-2:2006 BS 7176:2007 (Medium Hazard); BS 5852:2006 (Crib 5); NFP 92-501-1 (M1), DIN 4102-1 (B1), IMO Res. A 652 (16) Part 8 UNI 9174-UNI 8456 (C1), AM 18(NF D 60013) UNI 9175 Class 1 IM



CHARLES

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently.



CHARLES STUDIO DESIGN AVAILABLE AT SELECTED DISTRIBUTORS

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently. *Extended delivery time



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

AQUARIUS, BLAZER, CRISP, FAME, SYNERGY

wool 100%, weight 370 g/m² ± 5%, abrasion 60 000 Martindale cycles (BS 5690), resistance to pilling > 4, (BS EN ISO 12945-2:2000), light fastness 5 (ISO 105 - B02:2013), non-flammability certificate (BS EN 1021-1; BS EN 1021-2; BS7176:2007 Low Hazard) Fabric available until 31.12.2018



CRISP




96% wool, 5% polyamide weight: 450 g/m² abrasion: 200 000 Martindale cycles (EN ISO 12947-2) resistance to piling: 4 (EN ISO 12945-2) light fastness: 5-7 (EN ISO 105-B02) rubbing fastness: 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1&2; BS 5852:2006 (Crib 5); BS 5852 0&1; UNI 9175 class 1 IM; Calif. Bull. 117-E class 1 cleaning: dry cleaning

[illegible]

IV PRICE GROUP

REMIX

REMIX

Composition: 90% wool, 10% nylon Weight: ok 300 g/m2 Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021 - 1/2 BS 5852 Part 1 Onorm B1/Q1 UNI 9175 IMO A.652(16) Crib 5 and B2 Producer: kvadrat Denmark



V PRICE GROUP - STUDIO DESIGN

STEELCUT TRIO 2 , TURNBERRY , TROON , ACCESSOIRE

STEELCUT TRIO 2

STUDIO DESIGN

Composition: 90% wool, 10% nylon; Abrasion Resistance 100 000 Martindale cycles; Fastness to Rubbing 3-4 (EN ISO 12945); Light Fastness: 5-7 (ISO 105-B02) Flammability: EN 1021-1/2; BS 5852 part 1; DIN 4102 B2; Önorm B1/Q1; NF D 60 D13; UNI 9175 11M; US Cal. Bull. 117, –2013; IMO FTP Code 2010: Part 8



TURNBERRY

STUDIO DESIGN

Composition: 100% wool; Weight: 588 g/m2 ± 5%; Abrasion Resistance: 43 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5



TROON

STUDIO DESIGN


Composition 92% wool, 7% nylon; Weight: 37 g/m2 ± 5%; Abrasion Resistance: 60 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5



ACCESSOIRE

STUDIO DESIGN

Composition: 85% wool 15% polyamide, Weight: 350 g/m2 +/- 5%, Abrasion Resistance 50 000 Martindale cycles; Fastness to Rubbing: 4 (EN ISO 105-C06); Light Fastness: 5-7 (EN ISO 105-B02); Flammability: BS EN 1021-1 BS EN 1021 - 2



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.