

II PRICE GROUP

ROCCIA, CHARLES, CHARLES STUDIO DESIGN

ROCCIA

100% polyester-TREVIRA CS weight 250g/m2 +/-5%, abrasion 70 000 Martindale cycles (UNI EN ISO 12947/2), resistance to pilling 6 (EN ISO 12945/2), light fastness 6 (EN ISO 105-B02), fastness to rubbing wet: 4 (UNI EN ISO 105-X12) dry: 5 (UNI EN ISO 105-X12), non-flammability certificate: EN 1021-1:2006 EN 1021-2:2006 BS 7176:2007 (Medium Hazard); BS 5852:2006 (Crib 5); NFP 92-501-1 (M1), DIN 4102-1 (B1), IMO Res. A 652 (16) Part 8 UNI 9174-UNI 8456 (C1), AM 18/NF D 80013 UNI 9175 Class 1 IM



CHARLES

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently.



CHARLES STUDIO DESIGN AVAILABLE AT SELECTED DISTRIBUTORS

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90,000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently. *Extended delivery time



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

III PRICE GROUP

BLAZER, CRISP, FAME, SYNERGY

BLAZER

virgin wool 100%, Weight 460g/m2 +/-5%, abrasion resistance 50 000 Martindale cycles, fastness to pilling 4 (BS EN ISO 12945-2:2000), light fastness 5 (ISO 105-B02:1990); non-flammability certificate: BS EN 1021-1:2006, BS EN 1021-2:2006, BS7176:2007 Low Hazard Fabrics CUZ14, CUZ32, CUZ27 only available till the end of the year



CRISP

93% wool, 7% polyamide weight: 328 g/m2 abrasion: 200000 Martindale cycles (EN ISO 12947-2) resistance to piling 4-5 (EN ISO 12945-2) light fastness 5-7 (EN ISO 105-B02) rubbing fastness 4-5 (EN ISO 105x12 (wet/dry)) non-flammability: EN 1021-1,2; BS 5852 0&1; Calif. Bull. 117-E class 1; IMO MS c307(89)Annex 1 part 8; MED certificate IMO



FAME

95% wool, 5% polyamide weight: 450 g/m2 abrasion: 200 000 Martindale cycles (EN ISO 12947-2) resistance to piling: 4 (EN ISO 12945-2) light fastness: 5-7 (EN ISO 105-B02) rubbing fastness: 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1&2; BS 5852:2006 (Crib 5); BS 5852 0&1; UNI 9175 class 1 IM; Calif. Bull. 117-E class 1 cleaning: dry cleaning



SYNERGY

Composition: virgin wool 95%, polyamide 5%; Weight: 400g/m² ±5% Abrasion Resistance > 100 000 Martindale cycles, Fastness to Rubbing: 4 (ISO 105-X12) Light Fastness: 5 (ISO 105-B02) Flammability: EN 1021-1&2 Cigarette & Match NF D 60-013 UNI 9175 Classe 1 IM BS 7176 Low Hazard




IV PRICE GROUP

REMIX, LEATHER


REMIX

Composition: 90% wool, 10% nylon Weight: ok 300 g/m² Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021 - 1/2 BS 5852 Part 1 Onom B1/Q1 UNI 9175 IMO A.052(16) Crib 5 and B2 Producer: kvadrat, Denmark



LEATHER

size Ca. 5m², thickness >0.9mm-1.1mm, wet rub tests >250 (BS EN ISO 11640: 1998) dry rub tests >500 (EN ISO 11640:1998) flex resistance > 50 000 cycles (BS EN ISO 5402:2002), PCP und CFC used during tanning proces, natural colour variations may occur, non-flammability certificate (UNI EN 1021-1:2006, UNI EN 1021-2:2006)



METAL

METAL

METAL

colors frames

