



### III PRICE GROUP

AQUARIUS, BLAZER, SILVERTEX, CRISP, FAME, SYNERGY

#### AQUARIUS

wool 100%, weight 370 g/m<sup>2</sup> ± 5%, abrasion 60 000 Martindale cycles (BS 5680), resistance to pilling > 4, (BS:EN ISO 12945-2:2000), light fastness 5 (ISO 105 - B02:2013), non-flammability certificate (BS EN 1021-1; BS EN 1021-2; BS7176:2007 Low Hazard) Fabric available until 31.12.2018



#### BLAZER

virgin wool 100%, Weight 460g/m<sup>2</sup> +/-5%, abrasion resistance 50 000 Martindale cycles, fastness to pilling 4 (BS:EN ISO 12945-2:2000), light fastness 5 (ISO 105-B02:1999); non-flammability certificate: BS EN 1021-1:2006, BS EN 1021-2:2006, BS7176:2007 Low Hazard Fabrics CUZ14, CUZ32, CUZ27 only available till the end of the year



#### SILVERTEX

surface-100% Vinyl, basic material - 100% Polyester Hi-Loft2, weight 685g/m<sup>2</sup>, abrasion 300 000 Martindale cycles (EN ISO 12947-1999 Part 2), light fastness >7, non-flammability certificate (BS EN 1021-1/2, EN 1021/2, EN 71-2, IMO A 652(16)8.2-8.3, FMVSS302)



#### CRISP

93% wool, 7% polyamide weight: 328 g/m<sup>2</sup> abrasion: 200000 Martindale cycles (EN ISO 12947-2) resistance to piling 4-5 (EN ISO 12945-2) light fastness 5-7 (EN ISO 105-B02) rubbing fastness 4-5 (EN ISO 105x12 (wet/dry)) non-flammability: EN 1021-1,2; BS 5852 0&1; Calif. Bull.117-E class 1; IMO MS c307(88)Annex: 1 part 6; MED certificate IMO



#### FAME

95% wool, 5% polyamide weight: 450 g/m<sup>2</sup> abrasion: 200 000 Martindale cycles (EN ISO 12947-2) resistance to piling: 4 (EN ISO 12945-2) light fastness: 5-7 (EN ISO 105-B02) rubbing fastness: 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1&2; BS 5852:2006 (Cnb 5); BS 5852 0&1; UNI 9175 class 1 IM; Calif. Bull.117-E class 1 cleaning: dry cleaning



#### SYNERGY

Composition: virgin wool 95%, polyamide 5%; Weight: 400g/m<sup>2</sup> ±5% Abrasion Resistance > 100 000 Martindale cycles, Fastness to Rubbing: 4 (ISO 105-X12) Light Fastness: 5 (ISO 105-B02) Flammability: EN 1021-1&2 Cigarette & Match NF D 60-013 UNI 9175 Class 1 IM BS 7176 Low Hazard



TRON STUDIO DESIGN

Composition 92% wool, 7% nylon; Weight: 37 g/m2 ± 5%; Abrasion Resistance: 60 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5



ACCESSOIRE STUDIO DESIGN

Composition: 85% wool 15% polyamide, Weight: 350 g/m2 +/- 5%, Abrasion Resistance 50 000 Martindale cycles; Fastness to Rubbing: 4 (EN ISO 105-C06); Light Fastness: 5-7 (EN ISO 105-B02); Flammability: BS EN 1021-1 BS EN 1021 - 2



\*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

**IV PRICE GROUP**

REMIX, LEATHER

REMIX

Composition: 90% wool, 10% nylon Weight: ok 300 g/m2 Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021 - 1/2 BS 5852 Part 1 Onorm B1/Q1 UNI 9175 IMO A.652(16) Crib 5 and B2 Producer: kvadrat Denmark



LEATHER

size Ca.5m2, thickness >0,8mm-1,1mm, wet rub tests>250 (BS EN ISO 11640: 1998) dry rub tests >500 (EN ISO 11640:1998) flex resistance > 50 000 cycles (BS EN ISO 5402:2002), PCP und CFC used during tanning proces, natural colour variations may occur, non-flammability certificate (UNI EN 1021-1:2006, UNI EN 1021-2:2006)



**DECORATIVE STITCH**

DECORATIVE STITCH

DECORATIVE STITCH

The decorative stitch is available in the fabrics: Leather, Keimo, Valencia, Silvertex and is dedicated to the collections: CEO, Clubin, Dual, Eleven, In Access, Orle 3DH, Voo Voo.



**V PRICE GROUP - STUDIO DESIGN**

STEELCUT TRIO 2 , TURNBERRY , TROON , ACCESSOIRE

STEELCUT TRIO 2 **STUDIO DESIGN**

Composition: 90% wool, 10% nylon; Abrasion Resistance 100 000 Martindale cycles; Fastness to Rubbing 3-4 (EN ISO 12945); Light Fastness: 5-7 (ISO 105-B02) Flammability: EN 1021-1/2; BS 5852 part 1; DIN 4102 B2; Onorm B1/Q1; NF D 60 013; UNI 9175 11M; US Cal. Bull. 117, – 2013; IMO FTP Code 2010; Part 8



TURNBERRY **STUDIO DESIGN**

Composition: 100% wool; Weight: 586 g/m2 ± 5%; Abrasion Resistance: 43 000 cycle Martindale; Flammability: BS EN 1021 – 1; CRIB 5

