

I PRICE GROUP


BOND, KEIMO

BOND

polyester 100%, weight 250 g/m2 +/-5%, abrasion 100 000 Martindale cycles (EN ISO 12947-2), resistance to pilling 5 (EN ISO 12045-2), light fastness 6 (EN ISO 105-B02), non-flammability certificate (BS EN 1021-1) (BS EN 1021-2), CRIB 5, BS 7176 Medium Hazard, 1IM(UNI 9175)

KEIMO

surface 100% PU, basic material: 65% polyester, 35% cotton, weight 435 g/m2 +/-5%, abrasion >100 000 Martindale cycles (EN ISO 5470-2 method 1), light fastness >5(EN ISO 105 B 02), resistance to pilling 4-5 (EN ISO 105-X12), non-flammability certificat (BS 5852/DIN EN 1021-1)




II PRICE GROUP

FIGHTER, PASTEL, VALENCIA, ERA, ROCCIA, CHARLES, CHARLES STUDIO DESIGN

FIGHTER

polyester 100%, weight 365 g/m2, abrasion 130 000 cycles Martindale, resistance to pilling 4-5 (EN ISO 12945-2), light fastness >5 (EN ISO 105-B02), non-flammability certificate (BS EN 1021-1, BS EN 1021-2, BS 5852(part 10.1), Q1 UK, UNI 9175 Class 1 IEMME)



PASTEL

polyester 100% - TREVIRA CS, weight 260g/m2 +/-5%, abrasion 80 000 Martindale cycles, resistance to 5 (EN ISO 12945), light fastness 6 (EN ISO 105-B02), non-flammability certificate (EN 1021-1, EN 1021-2; Crib 5; BS 7176 Medium Hazard; C1, M1, B1, IMO A 652(16), IMO A 471(XII))




VALENCIA

surface: 100% vinyl, basic material - 100% polyester, weight 650g/m2, abrasion 300 000 Martindale cycles (UNE EN 14465:2004), non-flammability certificate (EN 1021-1; EN 1021-2; BS EN 1021-1/2; DIN EN 1021-1/2; IMO A 652(16) 8.2-8.3; FAR 25.853 b(4) AP.F Part 1(a)(1)(ii)), light fastness > 5 EN ISO 105-B02 antimicrobial protection, antibacterial protection, antimycotic protection, abrasion resistance, resistance to dirt(blood, urine)




ERA

Composition: Polyester 100%. Weight: 320g/m2 ±5%. Abrasion Resistance 100 000 Martindale cycles (EN ISO 12947:1998), Fastness to Rubbing 4 (ISO 105-X12:2002), Light Fastness 5 (EN ISO 105-B02:2014), Flammability (BS EN 1021-1 / BS EN 1021-2 / BS 7176:2007 Low Hazard)



ROCCIA

100% polyester-TREVIRA CS weight 250g/m2 +/-5%, abrasion 70 000 Martindale cycles (UNI EN ISO 12947/2), resistance to pilling 5 (EN ISO 12945/2), light fastness 6 (EN ISO 105-B02), fastness to rubbing wet:4 (UNI EN ISO 105-X12) dry:5 (UNI EN ISO 105-X12), non-flammability certificate: EN 1021-1:2009 EN 1021-2:2006 BS 7176:2007 (Medium Hazard); BS 5852:2008 (Crib 5); NFP 92-801-1 (M1), DIN 4102-1 (B1), IMO Res. A 652 (16) Part 8 UNI 9174-UNI 8456 (C1), AM 18(NF D 60013) UNI 9175 Class 1 IM



CHARLES

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90.000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently.



CHARLES STUDIO DESIGN AVAILABLE AT SELECTED DISTRIBUTORS

Composition: 100% Polyester Weight: 290 g/m2 Roll width: 140cm Abrasion Resistance 90.000 Martindale cycles (BS EN ISO 12947-2:1998) Pilling: 4 (EN ISO 12 945-2) Light Fastness 5 (ISO 105-B02) Fastness to Rubbing Wet: 4-5 (UNI EN ISO 105-X12) Dry: 4-5 (UNI EN ISO 105-X12) Flammability: -DIN EN 1021-1 *Charles fabric, due to its structure (long hair), can be arranged in a velour way while being used, creating the impression of different shades of upholstery. It is also susceptible to bending while sitting, which is why it should be combed very gently. *Extended delivery time




*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

III PRICE GROUP

AQUARIUS, BLAZER, SILVERTEX, CRISP, FAME, SYNERGY

AQUARIUS

wool 100%, weight 370 g/m2 ± 5%, abrasion 60 000 Martindale cycles (BS 5690), resistance to pilling > 4, (BS EN ISO 12945-2:2000), light fastness 5 (ISO 105 - B02:2013), non-flammability certificate (BS EN 1021-1; BS EN 1021-2; BS 7176:2007 Low Hazard) Fabric available until 31.12.2018



BLAZER

virgin wool 100%, Weight 460g/m2 +/-5%, abrasion resistance 50 000 Martindale cycles, fastness to pilling 4 (BS EN ISO 12945-2:2000), light fastness 5 (ISO 105-B02:1999); non-flammability certificate: BS EN 1021-1:2006, BS EN 1021-2:2006, BS 7176:2007 Low Hazard Fabrics CUZ14, CUZ32, CUZ27 only available till the end of the year



SILVERTEX

surface-100% Vinyl, basic material - 100% Polyester Hi-Loft, weight 685g/m2, abrasion 300 000 Martindale cycles (EN ISO 12947:1999 Part 2), light fastness >7, non-flammability certificate (BS EN 1021-1/2, EN 1021/2, EN 71-2, IMO A 652(16)8.2-8.3, FMVSS302)



CRISP

93% wool, 7% polyamide weight: 328 g/m2 abrasion: 200000 Martindale cycles (EN ISO 12947-2) resistance to pilling 4-5 (EN ISO 12945-2) light fastness 5-7 (EN ISO 105-B02) rubbing fastness 4-5 (EN ISO 105x12 (wet/dry) non-flammability: EN 1021-1,2; BS 5852 0&1; Calif. Bull. 117-E class 1; IMO MS c307(88)Annex 1 part 8; MED certificate IMO



FAME

95% wool, 5% polyamide weight: 450 g/m2 abrasion: 200 000 Martindale cycles (EN ISO 12947-2) resistance to piling: 4 (EN ISO 12945-2) light fastness: 5-7 (EN ISO 105-B02) rubbing fastness: 4-5 (EN ISO 105x12 (wet/dry)) non-flammability certificate: EN 1021-1&2; BS 5852:2009 (Crib 5); BS 5852 0&1; UNI 9175 class 1 IM; Calif.Bull.117-E class 1 cleaning: dry cleaning



SYNERGY

Composition: virgin wool 95%, polyamide 5%; Weight: 400g/m2 ±5% Abrasion Resistance > 100 000 Martindale cycles; Fastness to Rubbing: 4 (ISO 105-X12) Light Fastness: 5 (ISO 105-B02) Flammability: EN 1021-1&2 Cigarette & Match NF D 60-013 UNI 9175 Classe 1 IM BS 7176 Low Hazard



IV PRICE GROUP

REMIX, LEATHER, REMIX STUDIO DESIGN


REMIX

Composition: 90% wool, 10% nylon Weight: ok 300 g/m2 Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021 - 1/2 BS 5852 Part 1 Onom B1/Q1 UNI 9175 IMO A.682(18) Crib 5 and B2 Producer: kvadrat Denmark



LEATHER

size Ca.5m2, thickness >0.8mm-1.1mm, wet rub tests >250 (BS EN ISO 11640: 1998) dry rub tests >500 (EN ISO 11640:1998) flex resistance > 50 000 cycles (BS EN ISO 5402:2002), PCP und CFC used during tanning proces, natural colour variations may occur, non-flammability certificate (UNI EN 1021-1:2006, UNI EN 1021-2:2006)



REMIX STUDIO DESIGN AVAILABLE AT SELECTED DISTRIBUTORS

Composition: 90% wool, 10% nylon Weight: ok 300 g/m2 Abrasion Resistance: 100 000 Martindale cycles, Pilling: 3-4 (EN ISO 12945-2:2000) Light Fastness: 5-7 (ISO 105-B02:2000) Flammability: EN 1021-1/2 BS 5852 Part 1 Onorm B1/Q1 UNI 9175 IMO A.652(16) Crib 5 and B2 Producer: kvadrat Denmark *Extended delivery time



*Delivery term for orders for Studio Design fabrics is up to 4 weeks.

V PRICE GROUP - STUDIO DESIGN

STEELCUT TRIO 2, TURNBERRY, TROON, ACCESSOIRE


STEELCUT TRIO 2 STUDIO DESIGN

Composition: 90% wool, 10% nylon; Abrasion Resistance 100 000 Martindale cycles; Fastness to Rubbing 3-4 (EN ISO 12945); Light Fastness: 5-7 (ISO 105-B02) Flammability: EN 1021-1/2; BS 5852 part 1; DIN 4102 B2; Önorm B1/Q1; NF D 60 013; UNI 9175 11M; US Cal. Bull. 117. - 2013; IMO FTP Code 2010: Part 8



TURNBERRY STUDIO DESIGN

Composition: 100% wool; Weight: 586 g/m2 ± 5%; Abrasion Resistance: 43 000 cycle Martindale; Flammability: BS EN 1021 - 1; CRIB 5



TROON STUDIO DESIGN

Composition 92% wool, 7% nylon; Weight: 37 g/m2 ± 5%; Abrasion Resistance: 60 000 cycle Martindale; Flammability: BS EN 1021 - 1; CRIB 5



ACCESSOIRE STUDIO DESIGN

Composition: 85% wool 15% polyamide, Weight: 350 g/m2 +/- 5%, Abrasion Resistance 50 000 Martindale cycles; Fastness to Rubbing: 4 (EN ISO 105-C06); Light Fastness: 5-7 (EN ISO 105-B02); Flammability: BS EN 1021-1 BS EN 1021 - 2

